

Fosterville Ltd,
The Recycling Centre,
John Acres Lane,
Sandygate,
Kingsteignton,
TQ12 3GP

Date: 10th July 2017

Test Report No STR: 537313

Page 1 of 1

Test requirements: To determine the compressive strength of masonry units in accordance with **BS EN 772-1: 2011**

Sample details:

Type of unit:	Brick
Laboratory Ref. No.:	S66965
Certificate of Sampling received:	No
Certificate enclosed:	No
Client Ref. No.:	Brick 1-3
Date and time cast:	Unknown
Date of receipt at Lab:	27/06/2017
Date of Test:	04/07/2017
Sampling location:	Unknown
Method of sampling:	N/A
Sampled by:	Client
Target specification:	BS EN 771-3: 2011
Number of Specimens:	3 (three)
Method of Conditioning:	Immersion - clause 7.3.5
Method of Surface Preparation:	Mortar Capping


RESULTS:

Specimen No.	Plan Dimensions (mm)		Load (N)	Individual Strength (N/mm ²)	Equivalent Air-Dried Compressive Strength (N/mm ²)	Normalized Compressive Strength (N/mm ²)
	Length	Width				
1	216.5	65.5	347100	24.5	29.4	39.7
2	216.0	65.5	281500	19.9	23.9	32.3
3	217.0	65.5	396000	27.9	33.5	45.2
Compressive Strength of Sample (N/mm ²)				24.1	28.9	39.1
Coefficient of Variation (%)				16.7	16.6	16.6

COMMENTS / DEPARTURE FROM SPECIFIED PROCEDURE

None

Report checked and approved by:



Aled Roberts
Concrete Team Manager